

TRND

Holmen TRND is the perfect paper if you dare to challenge conventions and have creative ambitions for your magazine. With a surface that is rough, raw and matte, your products get a completely new image.

TECHNICAL DATA

Target values subject to production variations. Updates will be done continuously.

Target value	Grammage g/m ²	Brightness % D65/10°	Bulk cm ³ /g ±0,05	a* D65/10°	b* D65/10°	Opacity %
Holmen TRND	70	80	1.6	-0.5	-2.5	97
	55	80	2.0	-0.5	-2.5	95
	60	80	2.0	-0.5	-2.5	96
	70	80	2.0	-0.5	-2.5	97
	80	80	2.0	-0.5	-2.5	98

Printing methods: Heatset, Coldset, Digital Inkjet and Waterless.

Updated 2020-04-20

Environment

ISO 14001, FSC® C020071, PEFC/05-33-134 and EU Ecolabel, Reach.

TRND

PRINTING RECOMMENDATIONS

Heatset

Print order	KCMY
Ink	MF or SC ink
Characteristic data	FOGRA 47, FOGRA 41
ICC-profile	PSO-Uncoated-ISO12647-eci.icc PSO-MFC-Paper-eci.icc
Screen ruling	133-150 lpi
Max tone value	260%

Coldset

Print order	CMYK
Ink	Coldset
Characteristic data	FOGRA 47
ICC-profile	PSO-Uncoated-ISO12647-eci.icc
Screen ruling	133-150 lpi
Max tone value	260%

Digital Inkjet

Characteristic data	FOGRA 39
ICC-profile	ISO-coated-v2-eci.icc
Screen ruling	150 lpi
Max tone value	270%

Recommended paper type and dot gain curve in line with ISO 12647-2 2013

Paper type	7
Dot gain curve	C

L* a* b* guideline values

ISO 13655 D50 2° M1

Measuring instrument

Techkon SpectroDens LED Premium

L* a* b* target values D50

	L*	a*	b*	Fluorescence
Paper type 7 white Background	89+/-3	0+/-2	3+/-2	
Holmen TRND 1.6 and 2.0	89	2.4	-3.8	Low